Technical Data Sheet

Farapol Jam Chemical Indus. Co.

FARAPOL C 9011

Product Description and Applications

Farapol C 9011 is a specially and commercial formulated Cobalt Octoate for unsaturated polyester resins, epoxy vinyl ester resins and their derivatives.

Certificates and Approvals

Farapol Jam Chemical Industrial Company carries out the production, quality control, and distribution of this product in compliance with ISO 9001, 14001, 45001, 10002, 10004, 10015, and 17065 standards.

Typical Liquid Properties

Property @ 25 ºC	*Unit*	*Specification*	*Method*
Metal Content	%	10 ± 0.4	BS EN ISO 4619(2010)
Viscosity @ 23°C (F/C) No. 4	s	30-60	ASTM D 1200(2023)
State	-	Semi-viscous liquid	visual
Color	-	Violet color	visual
Specific Gravity	relative	0.950- 1.000	BS EN ISO 2811-1(2011)

Handling, Storage and Stability

FARAPOL C 9011 is an organic metallic salt dissolved in white spirit solvent. Hence, it should be stored indoors in a dry place at a temperature between 5 and 30°C. Keep always in the original, unopened, and undamaged containers. Avoid keeping material exposed to sunlight. On storage under the conditions mentioned above, the shelf life for FARAPOL C 9011 is 12 months.

Healthy and Safety

Avoid storing Metallic Driers and Peroxides in the same area. Safety Datasheets of the product are available on demand. The user is fully responsible for reviewing the material's Safety Data Sheet (SDS) and understanding proper handling procedures prior to using the product.

Packaging

FARAPOL C 9011 is supplied in 20 and 200 Kg steel barrels.

Notice

The information contained herein is provided in good faith and is with the best of our accurate knowledge, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments.
Please note that testing conditions may vary between different laboratories, and a tolerance of up to 5% should be expected in the test report. Farapol Jam Company reserves the right to modify the information in this document at its discretion. The latest version available on the Farapol website is considered valid, and any previous versions are void.

Document Registration

Pub. No: POL- F-76-33 Revision No.: rev. 01 Rev. Date: 01/27/2025

Contact Information

Tel: +98 21 26231019 Fax: +98 21 26231014

Site: www.farapol.com Email:info@farapol.com